

Blue Class B Engineer - Solid

Product Technical Information Sheet


Wienerberger Code	24331230
Production Plant	Kingsbury
Manufacture	Extruded/Wirecut
Configuration	Solid
Colour	Blue
Appearance	Smooth
Work Size (mm)	215 x 102.5 x 65
Pack Quantity	400 No.
Individual Dry Brick Weight (kg)	3.220

Technical Properties to BS EN 771-1

Size Tolerance (Mean/Range)	T2/R1
Gross Dry Density (kg/m ³ /Tolerance)	2190 (D1)
Compressive Strength (N/mm ²)	≥75
Thermal Conductivity (W/(m·K)) $\lambda_{10, dry, unit}$ value (EN 1745 tabulated: S1)	P=90% 0.79
Durability Designation	F2
Water Absorption (%)	≤7 (EN 772-7)
Initial Rate of Water Absorption (kg/(m ² ·min))	Min. 0.0 Max. 0.5
Active Soluble Salts	S2
Reaction to Fire	Class A1

Issue Date: 19/08/2020

Engineering bricks are specified for their physical characteristics and not their appearance. They have high compressive strength and low water absorption and are classified only by these properties. Their use for facing work should be avoided, as they are not subject to the same level of inspection for surface irregularities or colour variation as a facing brick. Where aesthetic performance is a major consideration, facing bricks must be used.



**BIM Objects
Download**



1000+ products to choose from



Expert help and advice



Comprehensive Design Services



Technical Support